



Renewable Roof Systems  
Wall Coatings



## **2100 Finish Coat**

### **PRODUCT DATA**

**Description:** **2100 Finish Coat** is a water borne, 100% acrylic coating and is a component of the fully reinforced and partially reinforced Acrylabs roof membrane. Utilizing advanced technology, **2100 Finish Coat** is formulated for maximum adhesion to asphalt, metal, modified bitumen, concrete, wood, EPDM, and most single ply membrane systems. **2100 Finish Coat** cures to a strong, durable finish that is easily maintained and is used as the final coats for Acrylabs Roof Systems.

**2100 Finish Coat** is available in 15 standard colors. Custom color matching is available, however, minimum order quantities apply.

**Application:** Can be brushed, rolled or sprayed. Final thickness of Finish Coat will vary depending on surface conditions (porosity, texture, etc.). A uniform dry film thickness of 10 mils (DFT) per coat, two coats minimum, is suggested to maintain a pinhole free membrane. Allow two to four hours between coats.

**2100 Finish Coat** is available in 5 and 55 gallon plastic containers.

### **TECHNICAL DATA**

WEIGHT PER GALLON	12 LBS.	ASTM D-1475
% SOLIDS BY WEIGHT	67.0%	ASTM D-1644-A
% SOLIDS BY VOLUME	53%	ASTM D-2697
PIGMENT VOLUME	43.0%	
VISCOSITY (Brookfield)	130-140 Ku	ASTM D-562-A
V.O.C.	<50 g/l	ASTM D3960-01
PH	8.6 -9.2	ASTM E70-97
FLASH POINT	N/A	
LOW TEMPERATURE FLEXIBILITY mandrel bend @ -57F		ASTM D522-93A
ELONGATION AT (break)	196% @ 73F	ASTM D-2370
TENSILE STRENGTH AT (psi)	236psi @ 73F	ASTM D-2370
WATER SWELLING	9.2	ASTM-D 471
FUNGI RESISTANCE	ZERO RATING	G-53
PERMEABILITY (20MILS)	21.9 PERMS	ASTM D1653
ACCELERATED WEATHERING	<i>NO EFFECT 2 YEARS</i>	ASTM G-53

For more detailed instructions, refer to our Installation Guide or consult Acrylabs Technical Department.