



ACRYLIC COATINGS

2100 Acrylic Finish Coat

PRODUCT DATA

2100 is a water born 100% acrylic coating for the construction market. Utilizing advanced technology the 2100 is formulated for maximum adhesion to asphalt, metal, modified bitumen, concrete, wood, EPDM, PUF, and most single ply membrane systems.

2100 cures to a strong durable finish that is easily maintained. 2100 is the finish coat for most ACRYLAB ROOF SYSTEMS.

2100 is available in 13 standard colors. Custom matches can be done, however minimum order quantities apply; consult ACRYLABS for more information.

Application: *can be brushed, rolled or sprayed. Final thickness of 2100 will vary depending on surface conditions (porosity, etc.). A uniform dry film thickness of 12 mils (DFT) is suggested to maintain a pinhole free membrane. Allow two to four hours between coats.*

2100 is available in 1, 5, and 55 gallon plastic containers.

For more detailed instructions refer to our Installation Guide or consult ACRYLABS, INC. technical department.



ACRYLIC COATINGS

2100 TECHNICAL DATA

TYPICAL PROPERTIES

WEIGHT PER GALLON	12.2 LBS.	ASTM D1475-90
% SOLIDS BY WEIGHT	68.0	ASTM D2369-97
% SOLIDS BY VOLUME	55.2	ASTM D2697-86
PIGMENT VOLUME	43.0%	
VISCOSITY	110-120 Ku	ASTM D562-01
V.O.C.	<100 g/l	ASTM D3960-01
PH	8.6 –9.2	ASTM E70-97
FLASH POINT	N/A	

TYPICAL PROPERTIES (20 mil DFT)

LOW TEMPERATURE FLEXIBILITY	Passes 1/8" mandrel bend	
ELONGATION AT MAX STRESS	240% @ 74F	ASTM C-734
	80% @ 0F	
ELONGATION AT BREAK	300% @ 74F	ASTM D-412
	130% @ 0F	
TENSILE STRENGTH AT MAX STRESS	250psi @ 74F	ASTM D-412
	760psi @ 0F	
TENSILE STRENGTH AT BREAK	235psi @ 74F	ASTM D-412
	690psi @ 0F	
RECOVERY AFTER 25% ELONGATION	65%	ASTM D-412
PERMEABILITY (20MILS)	<10 PERMS	ASTM E96-80
ACCELERATED WEATHERING	NO EFFECT 2 YEARS WEATHEROMETER	ASTM G-53

AcryLabs, 730 Commercial Lane, Honey Brook, PA 19344

Phone 610-273-1355, Fax 610-273-1357

www.acrylabs.com