



2500 Acrylic Trowel Grade

PRODUCT DATA

***2500** is formulated to adhere to any clean surface. **2500** is designed to seal the joints between masonry, brick, metal, wood and glass. **2500** trowel grade is also used to repair cracks in stucco and other masonry surfaces.*

***2500** is available in white only.*

***Application:** should be applied using a putty knife or trowel. Final thickness of **2500** will vary depending on the width and depth of the void. Allow four to eight hours between coats. Dry time will vary with the thickness of the application.*

***2500** is available in 1 and 5 gallon plastic containers.*

For more detailed instructions refer to our Installation Guide or consult ACRYLABS, INC. technical department.



ACRYLIC COATINGS

2500 TECHNICAL DATA

TYPICAL PROPERTIES

WEIGHT PER GALLON	9.6 LBS.
% SOLIDS BY WEIGHT	67.3%
% SOLIDS BY VOLUME	61.7%
VISCOSITY: CENTIPOSIES AT 77 DEGREES BROOKFIELD (HBT)	78000 +- 5000
RHEOLOGICAL CHARACTERISTICS	THIXOTROPIC
CONSISTENCY	BRUSHABLE PASTE
FLASH POINT	N/A
LOW TEMPERATURE FLEXABILITY	ASTM D-746
SERVICE TEMPERATURE RANGE	-30F TO 180F
SHELF LIFE	2 YEAR MINIMUM
VEHICLE TYPE	ELASTOMERIC
V.O.C. CONTENT	82.4 g/l (0.66 lbs./gal)

AcryLabs, 730 Commercial Lane, Honey Brook, PA 19344
Phone 610-273-1355, Fax 610-273-1357

www.acrylabs.com